

Release: 07.09.2023

PETRALANA[®]
from nature

TECHNICAL DATA SHEET



PETRATOP-H

Stone wool plates
with a bright veil for thermal,
sound absorption and fire
protection

OFFICIAL DOCUMENTATION:

Declaration of Performance:
Nr PTRL-DoP/MW/23/129
Nr PTRL-DoP/MW/23/130



1454-CPR-1021

APPLICATION:

ceilings above garages

basements

FACTORY:

PETRALANA S.A.
Konstytucji 74 Str
41-905 Bytom
Poland
+48 32 770 05 00
office@petralana.eu

PETRALANA.EU

Release: 07.09.2023

PETRALANA®

from nature

PRODUCT CODE
PETRATOP-H MW-EN13162-T5-DS(70,90)-CS(10)10-TR1-WS-WL(P)-MU1 (d=80-99 mm) PETRATOP-H MW-EN13162-T5-DS(70 90)-CS(10)10-TR1-WS-WL(P)-MU1-AW0,95 (d=100-250 mm)
DECLARED THERMAL CONDUCTIVITY COEFFICIENT λ_D
$\leq 0,034$ [W/(mK)]

DECLARED PARAMETERS				
PROPERTIES OF THE PRODUCT ACC. TO EN 13162	SYMBOL	CLASS OF TOLERANCE	UNITS	
Class for thickness tolerances	T	T5	-1 mm / +3 mm	[mm]
			- 1 % / +3 mm	[%mm]
Dimensional stability under 70° C and 90% humidity	DS(70,90)	$\leq 1,0$		[%]
Compressive stress at 10% deformation or compressive strength	CS(10/Y)	10		[kPa]
Tensile strength perpendicular to faces	TR	$\geq 1,0$		[kPa]
Point load at 5mm deformation	PL(5)	[-]		[N]
Short time water absorption	WS	$\leq 1,0$		[kg/m ²]
Long time water absorption	WL(P)	$\leq 3,0$		[kg/m ²]
Water vapour transmission	MU	MU1		[-]
Sound absorption index	AW	0,95 (d=100=-250 mm)		[-]
Air flow resistivity	AFr	[-]		[kPa s/m ²]
Reaction to fire	RfF	A1		Euroclass

DECLARED THERMAL RESISTANCE R_D																	
d [mm]	80	90	100	120	140	160	180	200	220	240	250	-	-	-	-	-	-
R_D [m ² K/W]	2,35	2,60	2,90	3,50	4,10	4,70	5,25	5,85	6,45	7,05	7,35	-	-	-	-	-	-

DIMENSIONS AND PACKING									
FORMAT OF PLATES			PACKAGES			PALLETS			
length	Width	Thickness	No. of plates in a package	Cover surface in a package	Volume of a package	No. of plates on a pallet	Cover surface of plates on a pallet	Volume of plates on a pallet	
[mm]	[mm]	[mm]	[pcs.]	[m ²]	[m ³]	[pcs.]	[m ²]	[m ³]	
1000	600	80	5	3,00	0,240	12	36,00	2,880	
		100	4	2,40	0,240	12	28,80	2,880	
		120	2	1,20	0,144	20	24,00	2,880	
		150	4	2,40	0,360	8	19,20	2,880	
		200	2	1,20	0,240	12	14,40	2,880	
		(*)	-	-	-	-	-	-	-
		(*)	-	-	-	-	-	-	-

(*) other thickness under request