

TECHNICAL DATA SHEET



OFFICIAL DOCUMENTATION:

Declaration of Performance:
No. PTRL-DoP/MW/15/03
No. PTRL-DoP/MW/15/17
No. PTRL-DoP/MW/15/16



APPLICATION:

external and partition walls insulated by ETICS system

external monolithic, prefabricated and brick walls

floors above garages, passages and basements

fire insulation of attics (reaction to fire classification A1)

PETRALANA S.A.
Konstytucji 74 Street
41-905 Bytom
Poland
+48 32 770 05 00
office@petralana.eu

PRODUCT CODE
PETRAFAS MW-EN13162-T5-DS(70,90)-CS(10)20-TR10-WS-WL(P)-MU1 (d=30-99 mm) PETRAFAS MW-EN13162-T5-DS(70,90)-CS(10)30-TR10-WS-WL(P)-MU1-AW1,00 (d=100-220 mm) PETRAFAS MW-EN13162-T5-DS(70,90)-CS(10)30-TR10-WS-WL(P)-MU1-AW1,00 (d=221-250 mm)
DECLARED THERMAL CONDUCTIVITY COEFFICIENT λ_D
$\leq 0,035$ [W/(mK)]

DECLARED PARAMETERS			
DECLARED PROPERTIES OF THE PRODUCT ACC. TO EN 13162:2012+A1:2015	SYMBOL	CLASS OR TOLERANCE	UNITS
Class for thickness tolerances	T	T5	-1 mm / +3 mm [mm]
			-1 % / +3 mm [%/mm]
Dimensional stability under 70 °C and 90% humidity	DS(70,90)	$\leq 1,0$	%
Compressive stress at 10% deformation	CS(10/Y)	20 (d=30-99 mm) 30 (d=100-250 mm)	[kPa]
Tensile strength perpendicular to faces	TR	$\geq 10,0$	[kPa]
Point load at 5mm deformation	PL(5)	NPD	[N]
Short time water absorption	WS	$\leq 1,0$	[kg/m ²]
Long time water absorption	WL(P)	$\leq 3,0$	[kg/m ²]
Water vapour transmission	MU	MU1	[-]
Air flow resistivity	AFr	NPD	[kPa s/m ²]
Reaction to fire	RtF	A1	Euroclass
Sound absorption	AW	1,00(d=100-250mm)	[-]

DECLARED THERMAL RESISTANCE R_D																	
d [mm]	50	60	80	100	120	140	150	160	180	200	220	240	250	-	-	-	-
R_D [m ² K/W]	1,40	1,70	2,25	2,85	3,40	4,00	4,25	4,55	5,10	5,70	6,25	6,85	7,10	-	-	-	-

DIMENSIONS AND PACKING								
FORMAT OF PLATES			PACKAGES			PALLETS		
Length	Width	Thickness	No. of plates in a package	Cover surface of a package	Volume of a package	No. of plates on a pallet	Cover surface of plates on a pallet	Volume of plates on a pallet
[mm]	[mm]	[mm]	[pcs.]	[m ²]	[m ³]	[pcs.]	[m ²]	[m ³]
1000	600	50	6	3,60	0,180	16	57,60	2,880
		60	5	3,00	0,180	16	48,00	2,880
		80	5	3,00	0,240	12	36,00	2,880
		100	3	1,80	0,180	16	28,80	2,880
		120	2	1,20	0,144	20	24,00	2,880
		140	2	1,20	0,168	16	19,20	2,688
		150	2	1,20	0,180	16	19,20	2,880
		160	2	1,20	0,192	12+16	33,60	5,376
		180	2	1,20	0,216	12	14,40	2,592
		200	2	1,20	0,240	12	14,40	2,880
		220	1	0,60	0,132	20	12,00	2,640
		240	1	0,60	0,144	20	12,00	2,880
		250	1	0,60	0,150	16+20	21,60	5,400
-	-	-	-	-	-	-	-	-